

**Amendments to the Claims:**

The listing of claims will replace all prior versions, and listings, of claims in the application:

**Listing of Claims:**

1 – 39. (Cancelled)

40. (currently amended) A process for treating a fluorine compound-containing gas, comprising:

contacting a gas stream containing at least one compound of carbon and fluorine, wherein the concentration of the at least one compound of carbon and fluorine is from 0.1% to 10% by volume, with a catalyst comprising alumina and 7.2 to 49.4 wt.% of nickel oxide, said catalyst containing a composite oxide of aluminum and nickel;

adding a hydrocarbon to the gas stream;

adding nitrogen to the gas stream;

adding steam or a reaction gas containing steam and oxygen to the gas stream;

effecting a hydrolysis reaction between the at least one compound of carbon and fluorine and the steam, thereby producing a treated gas containing hydrogen fluoride, and

spray washing the treated gas to neutralize or remove the hydrogen fluoride .

41. (Previously Presented) A process according to Claim 40, wherein the spray washing comprises washing the treated gas with water to remove the hydrogen fluoride.

42. (Previously Presented) A process according to Claim 40, wherein the spray washing comprises washing the treated gas with an alkaline solution or slurry to neutralize the hydrogen fluoride and other acidic compounds.

43. (Previously Presented) A process according to Claim 40, wherein the spray washing comprises washing the treated gas with water and subsequently neutralizing the water that has absorbed the hydrogen fluoride with an alkaline solution or slurry.

44. (Previously Presented) A process according to Claim 40, wherein the catalyst further comprises zinc oxide, and wherein a ratio of aluminum to a total of nickel and zinc is 50 to 99: 50 to 1 by atom.

45. (Previously Presented) A process according to Claim 40, wherein the catalyst consists essentially of alumina and nickel oxide and a composite oxide of aluminum and nickel.

46. (Previously Presented) A process according to Claim 40, wherein the at least one compound of carbon and fluorine is at least one compound selected from the group consisting of CF<sub>4</sub>, C<sub>2</sub>F<sub>6</sub>, C<sub>3</sub>F<sub>8</sub>, C<sub>4</sub>F<sub>8</sub>, and C<sub>5</sub>F<sub>8</sub>.

47. (Cancelled)

48. (currently amended) A method of treating a gas containing a perfluoro-compound, comprising:

contacting the gas containing a perfluoro-compound, wherein the perfluoro-compound is a compound of carbon and fluorine, in a concentration of from 0.1% to 10% by volume at a temperature of 400 to 800°C with a catalyst comprising aluminum oxide and 7.2 to 49.4 wt.% of nickel oxide, said catalyst containing a composite oxide of aluminum and nickel, in the presence of steam and nitrogen and a hydrocarbon , whereby the perfluoro-compound is decomposed by hydrolysis to produce a treated gas containing hydrogen fluoride and acidic compounds; and

contacting the treated gas with water to absorb the hydrogen fluoride and the acidic compounds from the treated gas.

49. (Previously Presented) A process according to Claim 48, wherein the perfluoro-compound is at least one compound selected from the group consisting of CF<sub>4</sub>, C<sub>2</sub>F<sub>6</sub>, C<sub>3</sub>F<sub>8</sub>, and C<sub>4</sub>F<sub>8</sub>.

50. (Previously Presented) A process according to Claim 48, wherein the catalyst further comprises zinc oxide, the balance being aluminum oxide.

51. (Previously Presented) A process according to Claim 48, wherein the catalyst consists essentially of alumina and nickel oxide and composite oxide of aluminum and nickel.

52 – 78. (Cancelled)

79. (Previously Presented) A process according to claim 40, wherein the fluorine compound-containing gas to be treated is used as etchants or cleaners for semiconductors.

80. (currently amended) A process for treating a fluorine compound-containing gas, comprising:

contacting a gas stream containing at least one compound of carbon and fluorine, wherein the concentration of the at least one compound of carbon and fluorine is 2 to 10% by volume, with a catalyst comprising alumina and 7.2 to 38.6 wt.% of nickel oxide said catalyst containing a composite oxide of aluminum and nickel;

adding a hydrocarbon to the gas stream;

adding nitrogen to the gas stream;

adding steam or a reaction gas containing steam and oxygen to the gas stream; and

effecting a hydrolysis reaction between the at least one compound of carbon and fluorine and the steam, thereby producing a treated gas containing hydrogen fluoride.

81. (currently amended) A process for treating a fluorine compound-containing gas, comprising:

contacting a gas stream containing at least one compound of carbon and fluorine at a temperature from about 400 °C to about 800°C, wherein the concentration of the at least one compound of carbon and fluorine is from 0.1% to

10% by volume, with a catalyst comprising alumina and 7.2 to 38.6 wt.% of nickel oxide said catalyst containing a composite oxide of aluminum and nickel,

adding a hydrocarbon to the gas stream;

adding nitrogen to the gas stream;

adding steam or a reaction gas containing steam and oxygen to the gas stream; and

effecting a hydrolysis reaction between the at least one compound of carbon and fluorine and the steam, thereby producing a treated gas containing hydrogen fluoride.

82. (Previously Presented) The process of claim 81, wherein said gas stream is contacted with said catalyst at a temperature from about 400 °C to about 700°C.

83. (currently amended) A process for treating a fluorine compound-containing gas, comprising:

contacting a gas stream containing at least one compound of carbon and fluorine at a temperature from about 400 °C to about 700°C, wherein the concentration of the at least one compound of carbon and fluorine is from 0.1% to 10% by volume, with a catalyst comprising alumina and about 20 to about 30 wt.% of nickel oxide said catalyst containing a composite oxide of aluminum and nickel,

adding a hydrocarbon to the gas stream;

adding nitrogen to the gas stream;

adding steam or a reaction gas containing steam and oxygen to the gas stream; and

effecting a hydrolysis reaction between the at least one compound of carbon and fluorine and the steam, thereby producing a treated gas containing hydrogen fluoride.

84. (Previously Presented) The process of claim 83, wherein said gas stream is contacted with said catalyst at a temperature from about 400 °C to about 700°C.

85. (Previously Presented) The process of claim 40, wherein said decomposition activity of the catalyst for the at least one compound of carbon and fluorine is maintained by the nickel oxide additive.

86. (Previously Presented) The process of claim 48, wherein said decomposition activity of the catalyst for the at least one compound of carbon and fluorine is maintained by the nickel oxide additive.

87. (Previously Presented) The process of claim 40, wherein said catalyst further comprises sulfur.

88. (Previously Presented) The process of claim 40, wherein said catalyst further comprises sulfate.

89. (Previously Presented) The process of claim 40, wherein said catalyst further comprises sulfur in an amount of from 0.1 to 20% by weight.